


www.prolightopto.com





ProLight PB2H-4MDE-HWFC 4W Power LED Technical Datasheet Version: 1.1

Main Applications

· Horticultural Lighting

· Accent and effect lighting

ProLight Opto PB2H Series

Features


- · Corrosion robustness
- · SMD 3535 ceramic package
- · Maximum drive current: 1200 mA
- · Wide viewing angle: 120° (Lambertian optical lens)
- · Radiometric flux: typ. 1500 mW @ 700mA ; typ. 781 mW @ 350mA
- · Photosynthetic Photon Flux: typ. 5.57 μmol/s @ 700mA ; typ. 2.90 μmol/s @ 350mA
- · Best JEDEC Moisture Sensitivity Level 1

Introduction

•Phenix 3535 qualifies as the JEDEC Level 1 MSL sensitivity level and suitable for SMD process, Pb_free reflow soldering capability, and full compliance with EU Reduction of Hazardous Substances (RoHS) legislation.



Emitter Mechanical Dimensions





Notes:

- 1. Drawing not to scale.
- 2. All dimensions are in millimeters.
- 3. Unless otherwise indicated, tolerances are $\pm\,0.1\text{mm}.$
- 4. Please do not solder the emitter by manual hand soldering, otherwise it will damage the emitter.
- 5. Please do not use a force of over 0.3kgf impact or pressure on the lens of the LED, otherwise it will cause a catastrophic failure.

*The appearance and specifications of the product may be modified for improvement without notice.



Flux Characteristics, $T_J = 25^{\circ}C$

	Radiometric Power (mW)				PPF (µmol/s)			
Part Number Emitter	@70	0mA	Refer @350mA	Refer @1000mA	@70	0mA	Refer @350mA	Refer @1000mA
	Min.	Тур.	Тур.	Тур.	Min.	Тур.	Тур.	Тур.
PB2H-4MDE-HWFC	1450	1500	781	2075	5.38	5.57	2.90	7.70

• ProLight maintains a tolerance of ± 7% on flux and power measurements.

• Please do not drive at rated current more than 1 second without proper heat sink.

Electrical Characteristics, T_J = 25°C

	Forward Voltage V _F (V)					Electrical Thermal Resistance Junction to
Color	Min.	@700mA Typ.	Max.	Refer @350mA Typ.	Refer @1000mA Typ.	Slug with efficiency is 73% (°C/W)
Royal Blue	2.8	2.9	3.2	2.8	3.0	2.8

ProLight maintains a tolerance of ± 0.1V for Voltage measurements.

Optical Characteristics at 700mA, $T_1 = 25^{\circ}C$

					Total	
Radiation		Domii	nant Wavelen	included Angle (degrees)	Viewing Angle (degrees)	
Pattern	Color	Min.	Тур.	Max.	θ _{0.90V}	2 θ _{1/2}
Lambertian	Royal Blue	448 nm	452 nm	458 nm	170	120

ProLight maintains a tolerance of ± 1nm for dominant wavelength measurements.



Absolute Maximum Ratings

Parameter	Royal Blue		
DC Forward Current (mA)	1200		
Peak Pulsed Forward Current (mA)	1500 (less than 1/10 duty cycle@1KHz)		
ESD Sensitivity (HBM per MIL-STD-883E Method 3015.7)	2KV		
LED Junction Temperature	120°C		
Operating Board Temperature at Maximum DC Forward Current	-40°C - 105°C		
Storage Temperature	-40°C - 120°C		
Soldering Temperature	JEDEC 020c 260°C		
Allowable Reflow Cycles	3		
Reverse Voltage	Not designed to be driven in reverse bias		

Radiometric Power Bin Structure at 700mA

Col	or	Bin Code	Radiometric Min.	Power (mW) Max.	PPF (µ Min.	ımol/s) Max.	PPF/W (µmol/J) Typ.	Available Color Bins
		н	1450	1500	5.38	5.57	2.70	All
Royal	Blue	J	1500	1550	5.57	5.75	-	All
		К	1550	1640	5.75	6.08	-	【1】

• ProLight maintains a tolerance of \pm 7% on flux and power measurements.

• The flux bin of the product may be modified for improvement without notice.

• ^[1] The rest of color bins are not 100% ready for order currently. Please ask for quote and order possibility.



Dominant Wavelength Bin Structure at 700mA

Color	Bin Code	Minimum Dominant Wavelength (nm)	Maximum Dominant Wavelength (nm)
Royal Blue	5	448	453
	6	453	458

• ProLight maintains a tolerance of ± 1nm for dominant wavelength measurements.

Forward Voltage Bin Structure at 700mA


Color	Bin Code	Minimum Voltage (V)	Maximum Voltage (V)
	А	2.8	2.9
Devel Plue	В	2.9	3.0
Royal Blue	D	3.0	3.1
	E	3.1	3.2

• ProLight maintains a tolerance of ± 0.1V for Voltage measurements.




Color Spectrum, T_J = 25°C

1. Royal Blue




Light Output Characteristics

Relative Light Output vs. Junction Temperature at 700mA






Forward Current Characteristics, $T_J = 25^{\circ}C$




Thermal Pad Temperature vs. Maximum Forward Current





Typical Representative Spatial Radiation Pattern



2024/11 | DS-1774



Moisture Sensitivity Level - JEDEC Level 1

				Soak Req	uirements	
Level	Floo	r Life	Stan	dard	Accelerated	Environment
	Time	Conditions	Time (hours)	Conditions	Time (hours)	Conditions
1	Unlimited	≤30 [°] C / 85% RH	168 +5/-0	85°C / 85% RH	NA	NA

- The standard soak time includes a default value of 24 hours for semiconductor manufature's exposure time (MET) between bake and bag and includes the maximum time allowed out of the bag at the distributor's facility.
- Table below presents the moisture sensitivity level definitions per IPC/JEDEC's J-STD-020C.

			Soak Requirements				
Level	Floor	r Life	Stan	dard	Accelerated	Environment	
	Time	Conditions	Time (hours)	Conditions	Time (hours)	Conditions	
1	Unlimited	≤30°C / 85% RH	168 +5/-0	85°C / 85% RH	NA	NA	
2	1 year	≤30°C / 60% RH	168 +5/-0	85°C / 60% RH	NA	NA	
2a	4 weeks	≤30°C / 60% RH	696 +5/-0	30°C / 60% RH	120 +1/-0	60°C / 60% RH	
3	168 hours	≤30°C / 60% RH	192 +5/-0	30°C / 60% RH	40 +1/-0	60°C / 60% RH	
4	72 hours	≤30°C / 60% RH	96 +2/-0	30°C / 60% RH	20 +0.5/-0	60°C / 60% RH	
5	48 hours	≤30°C / 60% RH	72 +2/-0	30°C / 60% RH	15 +0.5/-0	60°C / 60% RH	
5a	24 hours	≤30°C / 60% RH	48 +2/-0	30°C / 60% RH	10 +0.5/-0	60°C / 60% RH	
6	Time on Label (TOL)	≤30°C / 60% RH	Time on Label (TOL)	30°C / 60% RH	NA	NA	



Qualification Reliability Testing

Stress Test	Stress Conditions	Stress Duration	Failure Criteria
Room Temperature Operating Life (RTOL)	25°C, I _F = max DC (Note 1)	1000 hours	Note 2
Wet High Temperature Operating Life (WHTOL)	85°C/60%RH, I _F = max DC (Note 1)	1000 hours	Note 2
Wet High Temperature Storage Life (WHTSL)	85°C/85%RH, non-operating	1000 hours	Note 2
High Temperature Storage Life (HTSL)	110°C, non-operating	1000 hours	Note 2
Low Temperature Storage Life (LTSL)	-40°C, non-operating	1000 hours	Note 2
Non-operating Temperature Cycle (TMCL)	-40°C to 120°C, 30 min. dwell, <5 min. transfer	200 cycles	Note 2
Mechanical Shock	1500 G, 0.5 msec. pulse, 5 shocks each 6 axis		Note 3
Natural Drop	On concrete from 1.2 m, 3X		Note 3
Variable Vibration Frequency	10-2000-10 Hz, log or linear sweep rate, 20 G about 1 min., 1.5 mm, 3X/axis		Note 3
Solder Heat Resistance (SHR)	260°C ± 5°C, 10 sec.		Note 3
Solderability	Steam age for 16 hrs., then solder dip at 260°C for 5 sec.		Solder coverage on lead

Notes:

1. Depending on the maximum derating curve.

2. Criteria for judging failure

Item	Test Condition	Criteria for Judgement		
item	Test Condition	Min.	Max.	
Forward Voltage (V _F)	I _F = max DC		Initial Level x 1.1	
Luminous Flux or Radiometric Power (Φ_V)	I _F = max DC	Initial Level x 0.7		
Reverse Current (I _R)	$V_R = 5V$		50 µA	


* The test is performed after the LED is cooled down to the room temperature.

3. A failure is an LED that is open or shorted.



Recommended Solder Pad Design

Standard Emitter




- All dimensions are in millimeters.
- Electrical isolation is required between Thermal Pad and Anode or Cathode Pad.



Reflow Soldering Condition


Profile Feature	Sn-Pb Eutectic Assembly	Pb-Free Assembly
Average Ramp-Up Rate	3°C / second max.	3°C / second max.
(T _{Smax} to T _P)	5 C/ Second max.	S C / Second max.
Preheat		
– Temperature Min (T _{Smin})	100°C	150°C
– Temperature Max (T _{Smax})	150°C	200°C
– Time (t _{smin} to t _{smax})	60-120 seconds	60-180 seconds
Time maintained above:		
– Temperature (T _L)	183°C	217°C
– Time (t _i)	60-150 seconds	60-150 seconds
Peak/Classification Temperature (T _P)	240°C	260°C
Time Within 5°C of Actual Peak	10-30 seconds	20-40 seconds
Temperature (t _p)	10-20 Seconds	20-40 Seconds
Ramp-Down Rate	6°C/second max.	6°C/second max.
Time 25°C to Peak Temperature	6 minutes max.	8 minutes max.



- We recommend using the M705-S101-S4 solder paste from SMIC (Senju Metal Industry Co., Ltd.) for lead-free soldering.
- Do not use solder pastes with post reflow flux residue>47%. (58Bi-42Sn eutectic alloy, etc) This kind of solder pastes may cause a reliability problem to LED.
- All temperatures refer to topside of the package, measured on the package body surface.
- Repairing should not be done after the LEDs have been soldered. When repairing is unavoidable, a double-head soldering iron should be used. It should be confirmed beforehand whether the characteristics of the LEDs will or will not be damaged by repairing.
- Reflow soldering should not be done more than three times.
- When soldering, do not put stress on the LEDs during heating.
- After soldering, do not warp the circuit board.



Emitter Reel Packaging




Notes:

- 1. Drawing not to scale.
- 2. All dimensions are in millimeters.
- 3. Unless otherwise indicated, tolerances are $\pm\,0.1\text{mm}.$



Emitter Reel Packaging



Notes:

- 1. Empty component pockets sealed with top cover tape.
- 2. 500 pieces per reel.
- 3. Drawing not to scale.
- 4. All dimensions are in millimeters.



Precaution for Use

Storage


Please do not open the moisture barrier bag (MBB) more than one week. This may cause the leads of LED discoloration. We recommend storing ProLight's LEDs in a dry box after opening the MBB. The recommended storage conditions are temperature 5 to 30 °C and humidity less than 40% RH. It is also recommended to return the LEDs to the MBB and to reseal the MBB.


- We recommend using the M705-S101-S4 solder paste from SMIC (Senju Metal Industry Co., Ltd.) for lead-free soldering.
- Do not use solder pastes with post reflow flux residue>47%. (58Bi-42Sn eutectic alloy, etc) This kind of solder pastes may cause a reliability problem to LED.
- Any mechanical force or any excess vibration shall not be accepted to apply during cooling process to normal temperature after soldering.
- Please avoid rapid cooling after soldering.
- Components should not be mounted on warped direction of PCB.
- Repairing should not be done after the LEDs have been soldered. When repairing is unavoidable, a heat plate should be used. It should be confirmed beforehand whether the characteristics of the LEDs will or will not be damaged by repairing.
- This device should not be used in any type of fluid such as water, oil, organic solvent and etc. When cleaning is required, isopropyl alcohol should be used.
- When the LEDs are illuminating, operating current should be decide after considering the package maximum temperature.
- The appearance, specifications and flux bin of the product may be modified for improvement without notice. Please refer to the below website for the latest datasheets. <u>http://www.prolightopto.com/</u>

Handling of Silicone Lens LEDs

Notes for handling of silicone lens LEDs

- Please do not use a force of over 0.3kgf impact or pressure on the silicone lens, otherwise it will cause a catastrophic failure.
- The LEDs should only be picked up by making contact with the sides of the LED body.
- Avoid touching the silicone lens especially by sharp tools such as Tweezers.
- Avoid leaving fingerprints on the silicone lens.
- Please store the LEDs away from dusty areas or seal the product against dust.
- When populating boards in SMT production, there are basically no restrictions regarding the form of the pick and place nozzle, except that mechanical pressure on the silicone lens must be prevented.
- Please do not mold over the silicone lens with another resin. (epoxy, urethane, etc)





2024/11 | DS-1774



Disclaimers

ProLightopto Technology has made every reasonable effort to ensure the accuracy of the information in this datasheet. However, it should be understood that this information is for guidance only and does not constitute any offer or part of a contract.

ProLightopto Technology does not guarantee or accept any legal liability for the accuracy, completeness, or usefulness of any information, product, technology, or process disclosed in this datasheet. The company reserves the right to make changes or improvements to this datasheet at its discretion.

Unless this datasheet is incorporated into a formal contract, customers should not rely on the information as a binding commitment to any specifications or product parameters by ProLightopto Technology. Customers are advised to verify that the information is current and complete before entering into any contract or acknowledging any purchase order. Therefore, all products described herein are subject to ProLightopto Technology's terms and conditions at the time of order acknowledgment.

Unless agreed upon by contractual agreement, not all parameters of each product are necessarily tested. ProLightopto Technology does not warrant or grant any license, either expressed or implied, under its patent rights or the rights of others.

Reproduction of the information contained herein is permitted only if done without any modifications or alterations. Altering this information and reproducing it is considered an unfair and deceptive business practice. ProLightopto Technology is not responsible or liable for any such altered documentation.

Reselling ProLightopto Technology's products with statements that differ from or exceed the parameters specified by ProLightopto Technology voids all express or implied warranties for the associated product or service and is considered an unfair and deceptive business practice. ProLightopto Technology is not responsible or liable for any such statements.

ProLightopto Technology's products are not authorized for use as critical components in life support devices or systems without explicit written approval from ProLightopto Technology.

For the purposes of this disclaimer :

- 1. Life support devices or systems are defined as those intended for surgical implant into the body or those that support or sustain life. Their failure, when used according to instructions for use provided in the labeling, can reasonably be expected to result in significant injury to the user.
- 2. A critical component is any component of a life support device or system whose failure can reasonably be expected to cause the failure of the device or system, or to affect its safety or effectiveness.